



Contemporary Series

The Contemporary Series taps into today's trends with clean lines and less pronounced textures. Clay bricks with smooth faces and clean edges pull inspiration from elegant and stylish architecture, combining sleek looks with a full colour palette developed to coordinate with each other and with our stone veneer products.



Brick: Contemporary Series, Kentville and Sahara

Contemporary Series

PREMIUM COLOUR = ✦

STOCK ITEM PRODUCT = †

All other products = **MADE TO ORDER**

Manufactured in our Brampton, Ontario plant.

COLOURS



AUBURN MATT

Metric Norman
Premier Plus
Metric Jumbo



AUBURN SMOOTH

Metric Norman
Premier Plus
Metric Jumbo



BISTRO ✦

Metric Norman
Premier Plus
Metric Jumbo



CHARCOAL MATT ✦

Metric Norman
Premier Plus
Metric Jumbo



CHELSEA

Metric Norman
Premier Plus †
Metric Jumbo



CLARET

Metric Norman
Premier Plus †
Metric Jumbo




ESPRESSO

Metric Norman
Premier Plus †



KENTVILLE

Metric Norman
Premier Plus †
Metric Jumbo



LEATHERMAN

Metric Norman
Premier Plus †
Metric Jumbo



MANILLA MATT

Metric Norman
Premier Plus †
Metric Jumbo



MANILLA SMOOTH

Metric Norman
Premier Plus
Metric Jumbo



MOUNTAIN GRAY

Metric Norman
Premier Plus †
Metric Jumbo



NORDIC MATT

Metric Norman
Premier Plus †
Metric Jumbo



RAVEN ✦

Metric Norman
Premier Plus †
Metric Jumbo



REGENCY BROWN

Metric Norman
Premier Plus †
Metric Jumbo

MADE TO ORDER PRODUCTS: Minimum quantities and advance lead times must be considered. Pricing can vary according to product colour, size, and finish. Contact your Brampton Brick Sales Representative to discuss your project requirements prior to specifying.

Contemporary Series

PREMIUM COLOUR = ✚

STOCK ITEM PRODUCT = †

All other products = **MADE TO ORDER**

Manufactured in our Brampton, Ontario plant.

COLOURS



ROYAL GRAY

Metric Norman
Premier Plus †
Metric Jumbo



SAHARA

Metric Norman
Premier Plus
Metric Jumbo



SIENA MATT

Metric Norman
Premier Plus †
Metric Jumbo



SOLSTICE MATT

Metric Norman
Premier Plus
Metric Jumbo



SOLSTICE SMOOTH

Metric Norman
Premier Plus
Metric Jumbo



ST. JOHN

Metric Norman
Premier Plus
Metric Jumbo




TAHOE

Premier Plus †




VENETIAN

Metric Norman
Premier Plus †
Metric Jumbo




VICTORIAVILLE

Metric Norman
Premier Plus
Metric Jumbo



WESTVILLE

Metric Norman
Premier Plus
Metric Jumbo



WINDSOR

Premier Plus †

BRICK TEXTURE

Brampton Brick's Contemporary Series is manufactured in both matte and smooth texture.

MADE TO ORDER PRODUCTS: Minimum quantities and advance lead times must be considered. Pricing can vary according to product colour, size, and finish. Contact your Brampton Brick Sales Representative to discuss your project requirements prior to specifying.

Contemporary Series

SIZES



Metric Norman

290 x 57 x 90 mm
(11 1/2 x 2 1/4 x 3 1/2")

Bricks per square foot 4.6
Bricks per square metre 49.8



Premier Plus (PRP)

257 x 79 x 90 mm
(10 1/8 x 3 1/8 x 3 1/2")

Bricks per square foot 3.9
Bricks per square metre 42



Metric Jumbo

290 x 90 x 90 mm
(11 1/2 x 3 1/2 x 3 1/2")

Bricks per square foot 3
Bricks per square metre 33

PACKAGING SPECIFICATIONS

CONTEMPORARY SERIES	Weight/Cube (kg)	Weight/Cube (lb)	Weight/Brick (kg)	Weight/Brick (lb)	Bricks/Cube	Bricks/m ²	Bricks/ft ²
Metric Norman	1,170	2,574	2.5	5.5	468	49.8	4.6
Premier Plus	1,160	2,552	2.5	5.5	464	42.0	3.9
Metric Jumbo	945	2,079	3.5	7.7	270	33.0	3.0

NOTE

- Refer to your local building codes for proper installation of product.
- All Brampton Brick's clay brick products fully meet or exceed the latest version of the following standards: ASTM C216 and the Can/CSA A82 specifications.
- Sizes are available only in standard stock products. Please refer to individual colours for standard stock item sizes available.

TYPICAL CLAY BRICK PHYSICAL PROPERTIES

Physical Property		CSA	ASTM	Typical Brampton Brick Range	
				Metric Units	Imperial Units
Minimum Compressive Strength	Individual Average of 5	> 17.2 MPa > 20.7 MPa	> 2500 psi > 3000 psi	65 – 85 MPa	9400 – 12000 psi
24 Hour Cold Water Absorption*	Individual Average of 5	< 8.0% -	< 8.0% -	7.0% - 11.5%	
5 Hour Boiling Water Absorption	Individual Average of 5	< 17.0% -	< 20.0% < 17.0%	11.0% - 15.5%	
Saturation (C/B) Ratio*	Individual Average of 5	< 0.78 -	< 0.80 < 0.78	0.65 - 0.75	

Based on CSA A82 for Exterior Grade (EG), Type X and ASTM C216 for Severe Weather (SW), Type FBX

*Standards require conformance to at least one of the two criteria

LEED PROGRAM

Brampton Brick can help maximize the number of LEED credits you wish to achieve by producing a product specific to your design needs. Talk with your local Brampton Brick sales representative to learn how.

CODES & STANDARDS

CANADIAN STANDARDS GUIDE

Canadian Standards Association (CSA)

CSA A165 series, CSA Standards on Concrete Masonry Units

Masonry Construction for Buildings CSA A371

Fired Masonry Brick made from Clay or Shale CSA A82

Connectors for Masonry CSA A370

Mortar and Grout for Unit Masonry CSA A179

For the most current information on Canadian Codes and Standards, please visit: www.csagroup.org

AMERICAN STANDARDS GUIDE

American Society for Testing and Materials (ASTM)

ASTM C55, Standard Specification for Concrete Building Brick

Terminology for Clay Products C43

Test Methods for Sampling and Testing Brick and Structural Clay Tile C67

Standard Specification for Facing Brick (Solid Masonry Units made from Clay or Shale) C216

Specification for Mortar for Unit Masonry C270

Specification for Grout for Masonry C476

Standard Specification for Hollow Brick (Hollow Masonry Units made from Clay or Shale) C652

Standard Specification for Loadbearing Concrete Masonry Units C90

Standard Specification for Concrete Facing Brick and Other Concrete Masonry Facing Units C1634

For the most current information on American Codes and Standards, please visit: www.astm.org

MANUFACTURING TOLERANCES (CSA A82)

Brampton Brick produces to the FBX vs FBS (X vs S) <https://bitly.ws/V9tK>

SPECIFICATION	CATEGORY	TYPE X OR FBX TOLERANCE (mm)	TYPE S OR FBS (SMOOTH) TOLERANCE (mm)	TYPE S OR FBS (ROUGH) TOLERANCE (mm)
Maximum permissible variation from specified dimension	75mm and under	1.5	2.5	2.5
	75 to 100mm	2.5	3.0	3.0
	100 to 150mm	3.0	5.0	5.0
	150 to 200mm	4.0	6.0	6.0
	200 to 300mm	5.5	8.0	8.0
	300 to 400mm	7.0	10.0	10.0
Maximum permissible variation from job lot average dimension	75mm and under	1.5	1.5	2.5
	75 to 100mm	1.5	2.5	3.0
	100 to 150mm	2.5	2.5	5.0
	150 to 200mm	2.5	3.0	6.5
	200 to 300mm	3.0	5.0	8.0
	300 to 400mm	5.0	6.5	9.5
Maximum permissible warpage	200mm and under	1.5	2.5	2.5
	200 to 300mm	2.5	3.0	3.0
	300 to 400mm	3.0	4.0	4.0
Chippage	from edge	up to 5 % of brick = 3.0 to 6.5	up to 10 % of brick = 6.5 to 8.5	up to 15 % of brick = 8.0 to 11.0
	from edge	remaining 95 % of lot = 0 to 3.0	remaining 90 % of lot = 0 to 6.5	remaining 85 % of lot = 0 to 8.0
	from corner	up to 5 % of brick = 6.5 to 9.5	up to 10 % of brick = 9.5 to 13.0	up to 15 % of brick = 13.0 to 19.0
	from corner	remaining 95 % of lot = 0 to 6.5	remaining 90 % of lot = 0 to 9.5	remaining 85 % of lot = 0 to 13.0

INITIAL RATE OF ABSORPTION (IRA)

In this test, the bedding face of the brick is placed in a shallow tray of water for a period of one minute and the amount of water absorbed is calculated as in g/ (min. x 20 000mm²). The IRA is an indication of the potential bond between the brick unit and the mortar. The brick does require a certain absorption range in order to draw the water and cement into the surface voids and create a mechanical bond. If the IRA is too low, the lack of absorption can inhibit bond development. If the absorption is too high, the unit will draw the water out of the mortar too quickly, causing the mortar to lose plasticity and inhibit its strength and the bond development of the mortar. The IRA is an optional test and is not a requirement of the standard because there are more factors on site that can affect the IRA than simply the properties of the brick.

Corrective measures for brick with low IRA and or cold weather may include:

- Using type S mortar or increase amount of lime in mortar
- Keep brick dry and warm prior to installation
- Increase time between laying of the units and tooling

Corrective measures for brick with high IRA or hot weather may include:

- Pre-wet the units and/or keep them in shade prior to laying.
- Use admixtures which increase water retentively. [Ref #1]

SEALANTS & COATINGS

Many people think that putting water repellent on a clay brick masonry wall will help keep out the moisture and prolong the life of it. Sometimes water repellents are applied to address problems of excessive moisture or leakage in the wall. The fact is that a wall designed and constructed using best practice does not need to be treated with water repellent. Walls with excessive moisture issues are best addressed by fixing the root cause of the problem. Putting water repellents on the wall could lead to premature freeze thaw deterioration due to entrapment of the water inside the clay brick masonry, even though many of the repellents on the market today are said to be “breathable”. Although water repellents may reduce the surface absorption of moisture due to rain, the cause of deterioration is usually due to moisture sources that build up in the wall.

These sources include:

- Interior moisture, like warm interior air, condensing on a cold wall
- Exterior moisture that enters the wall through poor mortar joints, deteriorated sealants or improper application of moisture control features The entrapment effect is best seen in the graph below. Brick with and without water repellent were submerged in water for 24 hours and then allowed to dry with only their faces exposed. The brick without the water repellent dried twice as fast as the ones with water repellent.

Even though the water repellent did allow the brick to dry, the higher retained moisture content can make the difference in the long-term performance of the masonry wall. The effect of this moisture build up can be quite catastrophic. Brampton Brick does not recommend the use of masonry sealers.

- Water absorbed by the face is released through the face
- They do not seal large cracks or poor mortar joints
- They do not allow water that migrated behind the wall to exit the wall
- They do not replace good design and workmanship [Ref #2]

CLEANING OF NEW MASONRY

It is often necessary to clean new masonry to achieve the desired aesthetics. The first step is for the mason to try and avoid getting mortar smears on the face of the brick. If there are mortar smears, the easiest cleaning method is to use clear water and a brush. This method needs to be carried out within 24 hour, before the mortar has had time to set. If the mortar has set, then cleaning can be achieved by using a proprietary cleaning agent, high pressure water or a combination of both. If either of these methods is used, the cleaning should be carried out between 7 and 30 days of installation. 7 days allows the mortar to gain sufficient strength so that the mortar is not damaged during cleaning. If the mortar is allowed to set for more than 30 days, it becomes progressively more difficult to remove. If a proprietary cleaning agent is used, it is important that the brickwork is prewet so that the cleaning agent remains on the surface of the brickwork where it is most effective. Check with your brick manufacturer for recommendations on what cleaner is best suited for their product. If high pressure water is used, then the pressure should not exceed 4850 kPa (700 psi) at a 2 ft. minimum distance. Also use a fan nozzle with a spray angle of at least 60°. Use gentle strokes. As with all masonry cleaning projects, it is important to carry out the cleaning on an inconspicuous area of brickwork first to ensure that the desired results are achieved. Allow a day or two for the brickwork to dry before inspection. If the desired are achieved, proceed with cleaning the rest of the brickwork. For more information on cleaning of masonry, see BIA Technical Note 20. [Ref #3]

MANUFACTURING LOCATIONS

Brampton

225 Wanless Drive
Brampton, ON L7A 1E9

Markham

455 Rodick Road
Markham, ON L6G 1B2

Cambridge

1038 Rife Road
Cambridge, ON N1R 5S3

Detroit

51744 Pontiac Trail
Wixom, MI 48393

Hillsdale

2108 Flos Road Four East,
Hillsdale, ON L0L 1V0

References:

- [1] “Initial Rate of Absorption (IRA)”, Technical Notes, Pg 27. Clay Brick Association of Canada, PO Box 248 Burlington ON
- [2] “Use of Water Proofing Sealers”, Technical Notes, Pg 8. Clay Brick Association of Canada, PO Box 248 Burlington ON
- [3] “Cleaning of New Masonry”, Technical Notes, Pg 21. Clay Brick Association of Canada, PO Box 248 Burlington ON

BramptonBrick.com

CA - 1.800.GO.BRICK (462.7425) | US - 1.844.GO.BRICK (462.7425)

MEMBERS OF:



Product representations shown in this publication are intended to convey the general colour, texture and appearance of the product. Variations may occur in the manufacturing and printing process. Always select from current, physical samples.